



Ceramic Fiber Enterprises

CFE Moldable 2300, 2600, & 3000HH (Trowelable and/or Hand-Forming)



Applications

- ❖ Repair in furnaces, refractory cracks and voids. Any other areas requiring high temp insulation and sealing in a liquid mix, that is sticky.
- ❖ Added protection over the top of exposed anchors and components. Fill in around burner blocks and vacuum form shapes.



Technical Data

- ❖ Color: Light Grey to White
- ❖ Temperature Grades: CFE2300: 2300°F (1260°C)
CFE2600: 2600°F (1427°C)
CFE3000HH: 3000°F (1649°C)
- ❖ Recommend Operating Temperature: CFE2300: 2000°F (1093°C)
CFE2600: 2450°F (1343°C)
CFE3000HH: 2700°F (1482°C)
- ❖ 6 Month shelf life from Manuf. Date.
- ❖ Packaged in 1 & 5 gal pails, & 11oz Caulk tubes



Scott Marker
(574)-584-4839

Brett Lugo
(219)-255-8099

Richard Berry
(765)-720-8975

4455 W 300 N Crawfordsville, IN 47933